



Azarceram ceramic tower packings

Ceramic Raschig and Pall Rings

Chemical Composition

| SiO ₂ +AL ₂ O ₃ | Fe ₂ O ₃ | CaO | K ₂ O+Na ₂ O |
|--|--------------------------------|--------|------------------------------------|
| >90 % | <1 % | <1-2 % | <4 % |

Chemical and physical properties

| Index | Value |
|-------------------------|-------------|
| Acid resistance (%) | >99.8 |
| Water absorption (%) | <0.2 |
| Firing temperature (°c) | 1200 - 1300 |
| Crushing Strength (MPA) | >18 |



[Www.azarceram.com](http://www.azarceram.com)

+98 912 696 4510 Mr.Niazmandan

+98 912 123 6405 Mr.kazemi

All Rights Reserved By Azarceram Co.