



Azarceram ceramic tower packings


Ceramic Raschig and Pall Rings

Chemical Composition

SiO ₂ +AL ₂ O ₃	Fe ₂ O ₃	CaO	K ₂ O+Na ₂ O
>90 %	<1 %	<1-2 %	<4 %

Chemical and physical properties

Index	Value
Acid resistance (%)	>99.8
Water absorption (%)	<0.2
Firing temperature (°c)	1200 - 1300
Crushing Strength (MPA)	>18



www.azarceram.com

+98 912 696 4510 Mr.Niazmandan

+98 912 123 6405 Mr.kazemi

All Rights Reserved By Azarceram Co.